








 SAVVY COLORS SAVVYFIX 'C' DYES ON COTTON		GENERAL PROPERTIES							FASTNESS PROPERTIES							
		Solubility gms/l			Dyeing Properties		Fixation Temp. Exhaust Dyg.	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Bleaching			Perspiration ISO - 104 x E04		
		Temp.	Straight	30 pps / 1000 Common salt	Substantivity	Reactivity			Alteration	Stain	Hypochlorite	Hydrogen Peroxide		Alkaline	Acidic	
	Yellow M8G *Yellow 86	30°C.	70	40	L	M	40°C.	6-7	5	5	1	4-5	4	4-5	5	
	Yellow M4G *Yellow 22	30°C.	40	20	M	M	40°C.	6	5	5	1	3-4	5	4-5	5	
	Yellow MGR *Yellow 7	30°C.	30	5	H	M	40°C.	6	5	5	4-5	4-5	5	5	4	
	Golden Yellow MR *Yellow 44	30°C.	160	130	H	H	40°C.	6	5	5	2-3	4-5	5	4-5	4	
	Yellow M4R *Orange 14	30°C.	80	40	M	M	40°C.	5	5	5	1	3-4	5	4	4	
	Orange M2R *Orange 4	30°C.	180	160	M	M	30°C.	4	5	5	4	4	5	4-5	4	
	Red M5B *Red 2	30°C.	80	50	H	H	40°C.	4-5	5	4-5	1	2	4-5	5	3	
	Red M8B *Red 11	30°C.	50	10	H	M	30°C.	4-5	5	5	4	4-5	4	4-5	2	
	Pink MB *Red 74	30°C.	80	40	H	M	30°C.	4-5	4	4-5	2	3	3	4-5	5	