








 SAVVY COLORS		GENERAL PROPERTIES				FASTNESS PROPERTIES							
		Solubility gms/l		Light Fastness 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Perspiration ISO - 104 x E04		Bleaching				
		Temp.	Gms./Litre		Alteration	Stain	Alkaline	Acidic	Hypochlorite NaOCl		Peroxide		
SAVVYFIX 'ME' BIFUNCTIONAL ON COTTON													
	Yellow ME4GL *Yellow 160	50°C.	120	6	4-5	4-5	4-5	4-5	1	5	4	5	
	Golden Yellow MERL *Yellow 145	50°C.	100	5	5	5	3-4	3-4	4	4	3-4	3-4	
	Orange ME2RL *Orange 122	50°C.	55	5	5	5	4	4	2	5	4	5	
	Red ME4BL *Red 195	50°C.	100	5	4-5	4-5	4	4	3	3	4	4	
	Red ME3BL *Red 194	50°C.	100	5	4-5	4-5	4	3	4	3	4	4	
	Red ME6BL *Red 250	50°C.	80	5	4-5	4-5	4	4	3-4	3-4	4	4	
	Blue ME2RL *Red 248	50°C.	100	4	5	5	4	4	1	5	3	5	
	Navy Blue ME2GL *Blue 194	50°C.	120	4-5	4-5	4-5	3	3	1	4	3	3	
	Magenta MEBL	50°C.	120	5	4-5	4	4	3	4	4-5	4	3	