SAVVY COLORS		GENERAL PROPERTIES						FASTNESS PROPERTIES								
		Solubility gms/l			Dyeing Properties				Washing ISO - 104 x C04		Bleaching			Perspiration ISO - 104 x E04		
												Hydrogen Peroxide				
SAVVYFIX 'PN' DYES ON COTTON		Temp.	Straight	30 pts / 1000 Common salt	Substantivity	Reactivity	Fixation Temp. Exhaust Dyg.	Day Light 1:1 ISO - 105 - B02	Alteration	Stain	Hypochlorite	Alteration	Stain	Alkaline	Acidic
	Yellow P6GS *Yellow 95	30°C.	145	100	M	5	80°C	4	5	5	4	4	4-5	5	4-5
	Brill. Orange P2R	30°C.	145	100	M	5	80°C	4	5	5	4	4	4-5	5	4-5
	Brill. Red P4B *Red 245	30°C.	80	30	M	3	80°C	5	5	4-5	4	4	3	4	3
	Brill. Red P3B *Red 45	30°C.	150	120	M	3	80°C	5	4-5	5	4-5	4	4	4	4-5
	Brill. Red BPB *Red 24	30°C.	100	24	M	3	80°C	6	6	4-5	4-5	4	4	4	4-5
	Brill. BLUE P3R	30°C.	100	30	L	5	80°C	5	3-4	5	3	3-4	5	3	3-4
	Blue P6D	30°C.	100	30	L	5	80°C	4	3-4	5	4	3-4	4	4	3-4
	Brill Black PGR	30°C.	100	100	M	5	80°C	4	4	4-5	4	5	4-5	4	4-5