






 <b>SAVVY COLORS</b>		GENERAL PROPERTIES							FASTNESS PROPERTIES							
		Solubility gms/l			Dyeing Properties		Fixation Temp. Exhaust Dyg.	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Bleaching			Perspiration ISO - 104 x E04		
		Temp.	Straight	30 pts / 1000 Common salt	Substantivity	Reactivity			Alteration	Stain	Hyochlorite	Hydrogen Peroxide		Alkaline	Acidic	
	Yellow RR * <sub>1</sub>	30°C.	120	H	S	S	S	5	5	3-4		3-4	4			4
	Red RR *Red 106:1	30°C.	150	H	S	S	S	5	5	4	4	3	3	4	4	
	Blue RR *Blue 122	30°C.	100	H	S	S	S	4-5	4-5	3	3	1	4	3	3	
	Maroon RR * <sub>1</sub>	30°C.	30	M	S	S	S	3	2-3	3	1	1	3	3-4	3	
<b>SAVVYFIX 'RGB' DYES ON COTTON</b>																
	Yellow RGB	30°C.	120	H	S	S	S	4-5	5	3-4	3-4	4	4	3-4	3-4	
	Red RGB	30°C.	150	H	S	S	S	5	5	3-4	4	3-4	3	3-4	4	
	Blue RGB	30°C.	100	H	S	S	S	4-5	4-5	3-4	3	1-2	4	3-4	3	