









savvy colors SAVVY COLORS		Yellow LD		Red LD		Blue LD	
100% cotton fabric % of shade							
		0.5%	1%	0.5%	1%	0.5%	1%
Solubility (G/L)@ 50c temp plain water		>150		>150		>150	
Light Fastness ISO-105-B02	1 / 1 SD	4		4		3-4	
	1 / 6 SD	4		4		3	
WASHING							
ISO-105-C06-C2S 60Ctemp.	Effect	4		4		4	
	Stain (Co)	4		4		4	
ISO-105-C06-E2S 95Ctemp.	Effect	4		4		4	
	Stain (Co)	3 - 4		3 - 4		3 - 4	
ISO-105-C08 95Ctemp.	Effect	4 - 5		4 - 5		4 - 5	
	Stain (Co)	4		4		4	
Dry Cleaning ISO-10-D01		4 - 5		4 - 5		4 - 5	
Rubbing/Satness	Dry	4 - 5		4 - 5		4 - 5	
	Wet	4		4		4	
Chlorinated Water ISO-105-E03 (20ppm CL)		4		4		4	
Perspiration (Alk) ISO-105-E04	Effect	4		4		4	
	Stain (Co)	4		4		4	
Perspiration (Acid) ISO-105-E04	Effect	4		4		4	
	Stain (Co)	4		4		4	
SUITABILITY IN APPLICATION							
Exhaust Dyeing	60c temp.	+		+		+	
Cold Pad Batch with Silicate	8 - 12 hrs.	0		0		0	
Two Phase Steaming	90 sec.	-		-		-	
Thermofix	125c temp.	0		0		0	