SAVVY COLORS		GENERAL PROPERTIES						FASTNESS PROPERTIES								
SAVVYFIX 'C' DYES ON COTTON		Solubility gms/l			Dyeing Properties		Fixation Temp. Exhaust Dyg.	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Bleaching			Perspiration ISO - 104 x E04		
											Hypochlorite	Hydrogen Peroxide				
		Temp.	Straight	30 pts / 1000 Common salt	Substantivity	Reactivity			Alteration	Stain		Alteration	Stain	Alkaline	Acidic	
	Magenta MB *Violet 13	30°C.	20	5	H	H	30°C.	3-4	5	5	1	3	3	4-5	4-5	
	Violet C4R *Violet 12	30°C.	60	50	L	H	30°C.	5	5	4-5	3	3	3	4	4	
	Turq. Blue MGN *Blue 140	30°C.	130	-	H	H	40°C.	6	4-5	3-4	2-3	2-3	2	4	4	
	Brill Blue M4GD *Blue 168	30°C.	130	-	H	H	60°C.	6	4-5	4	2-3	2	2	4	4	
	Navy Blue M3R *Blue 9	30°C.	70	-	H	H	60°C.	5	5	4	3	1	3-4	4-5	3	
	Blue M2R *Blue 81	30°C.	100	60	H	H	40°C.	4	4	4	2	2	3	4	4	
	Blue MR *Blue 4	30°C.	80	40	L	H	60°C.	6	5	5	2	3-4	4-5	4-5	5	
	Brill Blue MX7R *Blue 161	30°C.	80	40	H	H	30°C.	3	4-5	4-5	-	-	-	-	-	