








 SAVVY COLORS SAVVYFIX 'H' DYES ON COTTON		GENERAL PROPERTIES							FASTNESS PROPERTIES						
		Solubility gms/l			Dyeing Properties		Fixation Temp. Exhaust Dyg.	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Bleaching			Perspiration ISO - 104 x E04	
		Temp.	Straight	30 pps / 1000 Common salt	Substantivity	Reactivity			Alteration	Stain	Hypochlorite	Hydrogen Peroxide		Alkaline	Acidic
	Yellow H6G *Yellow 95	30°C.	80	40	H	4	80°C.	5-6	5	5	1	3	4	4-5	4-5
	Yellow H7GL *Yellow 57A	30°C.	80	40	H	4	80°C.	5-6	5	5	1	3	4	4-5	4-5
	Brill Yellow H8G *Yellow 185	30°C.	70	40	H	4	60°C.	6	5	5	1	3	4	4-5	4-5
	Yellow H4G *Yellow 18	30°C.	130	100	L	4	80°C.	6-7	5	5	1	4	5	4-5	4-5
	Golden Yellow HR *Orange 12	30°C.	110	50	M	5	80°C.	6	5	5	3	4-5	5	4	5
	Orange H2R *Orange 13	30°C.	150	100	M	5	80°C.	4-5	5	5	4	4	4-5	5	4-5
	Red 6BX *Red 76	30°C.	80	40	L	2-3	60°C.	6	5	5	2	3-4	4-5	4-5	5
	Red H8B *Red 31	30°C.	80	10	H	2-3	80°C.	4-5	4-5	5	3-4	4	4-5	4	3-4
	Magenta HB *Violet 26	30°C.	100	80	M	4	80°C.	4	4-5	4-5	1	3	4	4	4