








 SAVVY COLORS SAVVYFIX 'HE' DYES ON COTTON		GENERAL PROPERTIES						FASTNESS PROPERTIES							
		Solubility gms/l			Dyeing Properties		Fixation Temp. Exhaust Dyg.	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Bleaching			Perspiration ISO - 104 x E04	
		Temp.	Straight	30 pts / 1000 Common salt	Substantivity	Reactivity			Alteration	Stain	Hypochlorite	Hydrogen Peroxide		Alkaline	Acidic
	Yellow HE6G *Yellow 135	30°C.	30	25	H	4	80°C.	4-5	5	5	1-2	4	4	3	4
	Yellow HE4G *Yellow 105	30°C.	25	20	H	5	80°C.	5-6	5	5	1-2	4-5	4-5	4-5	4-5
	Yellow HE4R *Yellow 84A	30°C.	70	60	H	4-5	80°C.	5-6	5	5	2-3	4-5	5	4-5	4-5
	Golden Yellow HER *Yellow 84	30°C.	80	60	H	4	80°C.	5	5	4-5	3-4	4-5	4	4-5	4
	Orange HE2R *Orange 84	30°C.	35	5	H	4-5	80°C.	3-4	4	5	4-5	4	4-5	4	4
	Red HE3B *Red 120	30°C.	150	140	H	4	80°C.	4-5	5	4	2-3	3-4	4-5	5	4-5
	Red HE7B *Red 141	30°C.	150	150	H	4	80°C.	4-5	5	5	3	4-5	4-5	5	4-5
	Red HE8B *Red 152	30°C.	160	160	H	5	80°C.	4-5	5	3	3-4	4-5	4-5	5	4-5
	Blue HERD *Blue 160	30°C.	60	60	H	3	80°C.	4	5	3	2	2	2-3	3-4	4