SAVVY COLORS		GENERAL PROPERTIES						FASTNESS PROPERTIES								
SAVVYFIX 'HE' DYES ON COTTON		Solubility gms/l			Dyeing Properties		Fixation Temp. Exhaust Dyg.	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Bleaching			Perspiration ISO - 104 x E04		
											Hypochlorite	Hydrogen Peroxide				
		Temp.	Straight	30 pts / 1000 Common salt	Substantivity	Reactivity			Alteration	Stain		Alteration	Stain	Alkaline	Acidic	
	Blue HEGN *-	30°C.	60	60	H	3	80°C.	4	5	3	2	2	2-3	3-4	4	
	Navy Blue HER *Blue 171	30°C.	60	60	H	4	80°C.	4	5	4-5	1-2	4	4-5	4	4-5	
	Navy Blue HE2R *Blue 172	30°C.	70	60	H	-	80°C.	4	4-5	3	2	3	3	4	5	
	Green HE4BD *Green 19	30°C.	120	60	H	4-5	80°C.	4	5	4-5	1	2-3	4-5	4-5	4	
	Black HEBL *-	30°C.	25	20	H	-	80°C.	4	5	5	3	4	4	4	4	