








 <b>SAVVY COLORS</b>		GENERAL PROPERTIES							FASTNESS PROPERTIES							
		Solubility gms/l			Dyeing Properties			Fixation Temp. Exhaust Dyg.	Dischargeability	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Hypochlorite NAOCL		Perspiration ISO - 104 x E04	
		Temp.	Straight	30 pts / 1000 Common salt	Substantivity	Reactivity	Alteration				Stain	Alteration	Stain	Alkaline	Acidic	
	Red RB *Red 198	30°C.	100	L	LS	S	S	G	6	3-4	5	1	4	4	5	
	Red BSID *Red 111	30°C.	100	L	LS	S	LS	G	5	4-5	5	1	5	5	4-5	
	Violet 5R *Violet 5	30°C.	100	M	S	S	S	P	6-7	4	5	5	3-4	4-5	4-5	
	Blue 3R *Blue 28	30°C.	100	H	S	S	S	G	7	4	5	3-4	5	5	4-5	
	Blue R *Blue 19	30°C.	100	H	S	S	S	G	6	4	5	3-4	5	4	3-4	
	Blue 220	30°C.	100	H	S	S	S	P	5	4	4-5	3-4	5	5	4-5	
	Blue 221	30°C.	100	H	S	S	S	P	4-5	4	4	3-4	5	5	3-4	
	Blue 222	30°C.	150	H	S	S	S	P	4-5	4-5	4-5	3-4	4	4	5	
	Brown GR *Brown 18	30°C.	100	M	S	S	S	G	6	4-5	5	1	5	4	5	