








 <b>SAVVY COLORS</b>		GENERAL PROPERTIES							FASTNESS PROPERTIES							
		Solubility gms/l			Dyeing Properties			Fixation Temp. Exhaust Dyg.	Dischargeability	Day Light 1:1 ISO - 105 - B02	Washing ISO - 104 x C04		Hypochlorite NAOCL		Perspiration ISO - 104 x E04	
		Temp.	Straight	30 pts / 1000 Common salt	Substantivity	Reactivity	Alteration				Stain	Alteration	Stain	Alkaline	Acidic	
	Turq. Blue G *Blue 21	30°C.	100	H	S	S	S	P	6	4-5	4-5	3-4	5	5	4-5	
	Turq. Blue H2GP *Blue 21/A	30°C.	100	H	S	S	S	P	6	4-5	4-5	3-4	5	5	4-5	
	Black B *Black 5	30°C.	100	H	S	S	S	G	5	4-5	5	1	5	5	4	
	Black RL *Blue 31	30°C.	100	H	S	S	S	F	7	4-5	5	3-4	5	5	4	
	Black HFGR *_	30°C.	120	H	S	S	S	G	5-6	5	4-5	2	5	5	4-5	
	Deep Black A-150 *_	30°C.	100	H	S	S	S	G	5	4-5	5	1	5	5	4	
	Deep Black WNN *_	30°C.	100	H	S	S	S	G	5	4-5	5	1	5	4-5	5	
	Super Black R *_	30°C.	100	H	S	S	S	G	5	4-5	5	1	5	4-5	5	
	Super Black G *_	30°C.	100	H	S	S	S	G	5	4-5	5	1	5	4-5	5	